



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 059 320 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
13.12.2000 Bulletin 2000/50

(51) Int Cl.7: **C08G 65/00, C08G 65/22,
C08G 65/32, C09D 171/02**

(21) Application number: **00304280.1**

(22) Date of filing: **22.05.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

- Yamaguchi, Kouichi,
Shin-Etsu Chemical Co., Ltd.
Usui-gun, Gunma-ken (JP)
- Kishita, Hirofumi, Shin-Etsu Chemical Co., Ltd.
Usui-gun, Gunma-ken (JP)

(30) Priority: **20.05.1999 JP 13959699**

(71) Applicant: **Shin-Etsu Chemical Co., Ltd.
Chiyoda-ku Tokyo 100 (JP)**

(74) Representative: **Stoner, Gerard Patrick et al
MEWBURN ELLIS
York House
23 Kingsway
London WC2B 6HP (GB)**

(72) Inventors:
• Yamaguchi, Hiromasa,
Shin-Etsu Chemical Co., Ltd.
Usui-gun, Gunma-ken (JP)

(54) **Perfluoropolyether-modified aminosilane, surface treating agent, and aminosilane-coated article**

(57) A novel perfluoropolyether-modified aminosilane cures into a film having improved water and oil re-

pellency, parting and anti-staining properties. A surface treating agent comprising the aminosilane, and an article with a coating of the aminosilane are also provided.

EP 1 059 320 A2

5

5

10

10

15

20

25



35

40



50


54



Herein, X is a hydrolyzable group, R¹ is lower alkyl, R² is hydrogen or lower alkyl, Q is CH₂CH₂CH₂ or CH₂CH₂NHCH₂CH₂CH₂, m is an integer of 6 to 50, n is equal to 2 or 3, and x and y each are an integer of 1 to 3. Because of good water and oil repellency, anti-staining properties, chemical resistance, lubricity, and parting properties, this perfluoropolyether-modified aminosilane can be utilized as a surface treating agent by coating onto surfaces of various substrates. However, the compound is not regarded optimal in performance because curing is rather slow.

[0008] In particular, since many tall buildings are constructed in the recent decades, the demand for the technology for imparting "stain resistance" or "ease of stain removal" for keeping glazing maintenance-free is increasing. There is a desire to have a material meeting such a demand.

[0009] We have found that a novel perfluoropolyether-modified aminosilane of the following general formula (1) obtained by a method to be described later has good water and oil repellency, anti-staining, chemical resistance, lubricity and separation properties. It can be used as a surface treating agent by coating to surfaces of various substrates. It cures into a coat which firmly bonds to a substrate so that the coat may sustain its effect over a long period of time.



Herein X¹ and X² each are a hydrolyzable group, R¹ and R² each are a monovalent hydrocarbon group of 1 to 6 carbon atoms, Q¹ and Q² each are a divalent organic group, m is an integer of 6 to 50, n is equal to 2 or 3, x and y each are an integer of 1 to 3.

[0010] The perfluoropolyether-modified aminosilane of formula (1) serving as a main component of the surface treating agent contains an amide linkage. The amide linkage is effective for the efficient orientation of modifying fluorine groups to the substrate surface. In this regard too, surface treating agents disclosed herein can be more effective than prior art agents.

[0011] Because of the inclusion of two hydrolyzable silyl groups, the perfluoropolyether-modified aminosilane of formula (1) is more reactive than the above-mentioned aminosilane of formula (4) and improved in cure and film formability.

[0012] Accordingly, the invention provides a novel perfluoropolyether-modified aminosilane of formula (1); a surface treating agent primarily comprising the perfluoropolyether-modified aminosilane and/or a partial hydrolytic condensate thereof; and an article having on its surface a cured coating primarily comprising the perfluoropolyether-modified aminosilane and/or a partial hydrolytic condensate thereof. Also, methods of preparation of the aminosilane and surface treating agent, and their use for surface treatment.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] The only figure, FIG. 1 is an IR spectrum diagram of the aminosilane obtained in Synthetic Example 1.

DETAILED INFORMATION

[0014] The perfluoropolyether-modified aminosilane of the invention is of the following general formula (1):

of two or more. It is desired to uniformly dissolve the above-mentioned components in the solvent.

[0024] Any well-known technique may be employed for treating surfaces of various substrates with the surface treating agent. For example, brush coating, dipping, spraying and evaporation techniques are useful. The treating conditions may be suitably chosen. As to the treating temperature, the optimum temperature varies with a particular treating technique. In the case of brush coating or dipping, the optimum temperature is in the range of room temperature to 120°C. As to the treating humidity, treatment under humid conditions is preferred because the reaction is promoted.

[0025] The substrate to which the surface treating agent of the invention is applicable includes a variety of materials such as paper, fabric, metals, glass, plastics, and ceramics.

[0026] The aminosilane of formula (1) forms a cured coating having improved water and oil repellency, parting properties and anti-staining properties. Exemplary applications of the surface treating agent that utilize these functions include water and oil repellants to be applied to paper, fabric, metals, glass, plastics, and ceramics; parting agents to be applied to adhesive tape, resin molding molds and rolls; and anti-staining agents to be applied to paper, fabric, metals, glass, plastics, and ceramics.

[0027] More illustrative applications are given below.

- anti-staining coating on the surface of anti-reflection film etc.,
- coating for preventing fingerprint and grease contamination on optical members such as eyeglass lenses and anti-reflection filters,
- water repellent, anti-staining coating on sanitary ware such as bathtubs, washbowls, toilets and lavatories,
- anti-staining coating on glass for the general industry and window glass and head lamp covers in vehicles such as automobiles, trains and aircraft,
- water repellent, anti-staining coating on building exteriors,
- coating for preventing oil contamination on kitchen ware,
- water repellent, anti-staining, anti-sticking coating in telephone booths,
- water and oil repellent, anti-fingerprint coating on artistic objects.

[0028] The cured coating on the surface of a substrate or article as mentioned above usually has a thickness of 0.1 nm to 5 µm, and especially 0.1 nm to 1 µm though not critical. The exact thickness may be properly selected for a particular type of substrate.

[0029] In addition to the above-described applications, an aminosilane of formula (1) may also be used for improving the flow and dispersion of paint additives, resin modifiers and inorganic fillers, and the lubricity of tape and film.


[0030] The perfluoropolyether-modified aminosilane of the invention can form a cured coating having good or improved water and oil repellence, parting properties and anti-staining properties.

EXAMPLE

[0031] Examples of the invention are given below by way of illustration and not by way of limitation.

Synthetic Example 1

[0032] A 200-ml, three-necked flask equipped with a thermometer, reflux condenser and stirrer was charged with 87.1 g of a perfluoropolyether-modified diallylamide of the formula (6) shown below, 40.5 g of m-xylene hexafluoride, and 0.094 g of a toluene solution of a chloroplatinic acid/vinylsiloxane complex (containing 2.40×10^{-6} mol of Pt), which were heated at 80°C and stirred. Trimethoxysilane, 7.3 g, was added dropwise to the reaction mixture, which was ripened for 3 hours at 85°C. After the disappearance of allyl groups in the reactant was confirmed by ¹H-NMR, the solvent and excess trimethoxysilane were distilled off in vacuum, leaving 84.0 g of a colorless clear liquid. The ¹H-NMR and IR spectroscopy data of the compound are shown below.



¹H-NMR (TMS standard, ppm)

-CH ₂ CH ₂ Si≡	0.6-0.7
-CH ₂ CH ₂ CH ₂ -	1.7-1.9
-CONCH ₂ CH ₂ -	3.3-3.5
-Si(OCH ₃) ₃	3.5-3.6


IR (KBr plate, liquid-membrane method, cm⁻¹, see FIG. 1)

2950-2820 (C-H)

1680 (CON)


1315-1090 (C-F)

[0033] From the above data, the compound was identified to have the following structural formula (7).





Synthetic Example 2

[0034] A compound of the following formula (8) was prepared by the same procedure as Synthetic Example 1 except that methyldimethoxysilane was used instead of the trimethoxysilane.





Synthetic Example 3

[0035] A compound of the following formula (10) was prepared by the same procedure as Synthetic Example 1 except that a compound of the following formula (9) was used instead of the perfluoropolyether-modified diallylamide of formula (6).



Synthetic Example 4 (Comparison)

[0036] A compound of the following formula (12) was prepared by the same procedure as Synthetic Example 1 except that a compound of the following formula (11) was used instead of the perfluoropolyether-modified diallylamide of formula (6).

Examples 1-1 to 1-3

[0037] In 97.0 g of perfluoro(2-butyltetrahydrofuran) was dissolved 3.0 g of the perfluoropolyether-modified aminosilane synthesized in each of Synthetic Examples 1 to 3. The solution was brush coated onto a glass plate of 2.5x10x0.5 cm. and allowed to stand for one hour in an atmosphere at 25°C and humidity 70% whereby the coating cured. This test specimen was examined by the following tests.

(1) Water and oil repellent test

Using a contact angle meter model A3 (Kyowa Kaimen Kagaku K.K.), the contact angle of the cured coating with water and n-hexadecane was measured as the rating of water and oil repellency.

(2) Parting test

A Cellophane adhesive tape strip (25 mm wide) was attached to the surface of the cured coating. Using a tensile tester, the tape strip was pulled and peeled at an angle of 180° and a rate of 300 mm/min. The force required for peeling was measured as the rating of parting property.

(3) Durability test

The surface of the cured coating was wiped 30 strokes with cellulose non-woven fabric under a predetermined load. Thereafter, the contact angle with water was measured as in test (1), from which durability was evaluated.

(4) Hydrolysis (film formation) test

In 97.0 g of perfluoro(2-butyltetrahydrofuran) was dissolved 3.0 g of the perfluoropolyether-modified aminosilane synthesized in each of Synthetic Examples 1 to 3. The solution was brush coated onto a glass plate of 2.5x10x0.5 cm. The coating was allowed to stand for 10 minutes in an atmosphere at 25°C and humidity 70% whereupon the uncured residue on the surface was wiped off with cellulose non-woven fabric. The contact angle of the coated glass surface with water was measured as the rating of hydrolysis or film formability.

[0038] The results of these tests (1) to (4) are shown in Table 1.

Comparative Example 1-1

[0039] A cured coating was obtained and tested as in Examples 1-1 to 1-3 except that the fluoroaminosilane synthesized in Synthetic Example 4 was used instead of the fluoroaminosilanes in Examples 1-1 to 1-3. The test results are also shown in Table 1.

Comparative Example 1-2

[0040] A cured coating was obtained and tested as in Examples 1-1 to 1-3 except that a compound of the following

formula (13) was used instead of the fluoroaminosilanes in Examples 1-1 to 1-3. The test results are also shown in Table 1.




Table 1

	Water and oil repellency (deg)		Parting	Durability	Hydrolysis
	Water	n-hexadecane	(g/25 mm)	(deg)	(deg)
E 1-1	114	72	19	113	110
E 1-2	115	74	20	113	108
E 1-3	118	75	16	114	113
CE 1-1	101	63	87	97	96
CE 1-2	110	72	20	101	87

The coating of Examples show water and oil repellency and parting (peeling or separation) property at least comparable to the prior art coating (Comparative Example 1-2) and are improved in durability and hydrolysis (or film formation). The coating of Comparative Example 1-1 is inferior in water and oil repellency and parting property to the coatings of Examples and unacceptable on practical use.

[0041] It is thus evident that perfluoropolyether-modified aminosilanes proposed herein can form a tough coating on a substrate surface and be applicable as a surface treating agent having good water and oil repellence and parting property in combination.

Examples 2-1 to 2-3

[0042] In 495.0 g of perfluoro(2-butyltetrahydrofuran) was dissolved 5.0 g of the perfluoropolyether-modified aminosilane synthesized in each of Synthetic Examples 1 to 3. Trifluoromethanesulfonic acid, 0.05 g, was added to the solution, followed by thorough agitation. An acrylic resin plate of 10x10x0.8 cm was dipped in the coating solution. The coating was allowed to stand for 2 hours in an atmosphere at 40°C and humidity 85% whereby the coating cured. The surface was wiped off with dry fabric. This test specimen was examined by the following tests.

(1) Water repellent test

Using a contact angle meter model A3 (Kyowa Kaimen Kagaku K.K.), the contact angle of the cured coating with water was measured as the rating of water repellency.

(2) Anti-staining test

About 30 g of a contaminant shown in Table 2 was poured onto the coated acrylic resin plate. It was examined how the contaminant stuck to the coating. The contaminant-applied plate was air dried at room temperature for 15 minutes and then wiped with dry fabric. It was examined how the contaminant was wiped off. Evaluation was made according to the following criterion:

Contaminant sticking

[0043]

O: little sticking

Δ: some sticking

X: heavy sticking

Contaminant wiping-off**[0044]**

O: light wiping

 Δ : difficult to wipe off, but no track

X: difficult to wipe off, with track left

[0045] The results are shown in Table 2.Comparative Example 2-1

[0046] A coating solution was prepared and examined as in Examples 2-1 to 2-3 except that the fluoroaminosilane synthesized in Synthetic Example 4 was used instead of the inventive aminosilane. The results are also shown in Table 2.

Comparative example 2-2

[0047] A coating solution was prepared and examined as in Examples 2-1 to 2-3 except that $C_8F_{17}CH_2CH_2Si(OCH_3)_3$ was used instead of the inventive aminosilane. The results are also shown in Table 2.

Comparative Example 2-3

[0048] Without applying the coating solution, the acrylic resin plate was examined as in Examples 2-1 to 2-3. The results are also shown in Table 2.

Table 2

	Water repellency (deg)	Anti-staining			
		Chinese ink		Squalane	
		Sticking	Wiping	Sticking	Wiping
E 2-1	114	O	O	O	O
E 2-2	114	O	Δ	O	O
E 2-3	117	O	O	O	O
CE 2-1	100	Δ	X	Δ	X
CE 2-2	104	Δ	Δ	Δ	Δ
CE 2-3	75	Δ	X	X	X

Examples 3-1 to 3-3

[0049] In 495.0 g of perfluorohexane was dissolved 5.0 g of the perfluoropolyether-modified aminosilane synthesized in each of Synthetic Examples 1 to 3. Trifluoromethanesulfonic acid, 0.05 g, was added to the solution, followed by thorough agitation. The coating solution was spin coated onto a glass lens. The coating was allowed to stand for 2 hours in an atmosphere at 40°C and humidity 85% whereby the coating cured. The surface was wiped off with dry fabric. This test specimen was examined by the following tests.

(1) Water repellent test

Using a contact angle meter model A3 (Kyowa Kaimen Kagaku K.K.), the contact angle of the coated lens with water was measured as the rating of water repellency.

(2) Anti-staining test

The forefinger was pressed against the coated lens for 5 seconds, leaving a fingerprint. The lens was observed to examine whether the fingerprint was definite or obscure. It was also examined how the fingerprint was wiped off with dry fabric. The evaluation was made according to the following criterion. The rating was an average of a 5-member panel.

Fingerprint marking**[0050]**

O: little fingerprint left
 X: definite fingerprint

Fingerprint wiping-off**[0051]**

O: light wiping
 Δ : difficult to wipe off, but no track
 X: difficult to wipe off, with track left

[0052] The results are shown in Table 3.Comparative Example 3-1

[0053] A coating solution was prepared and examined as in Examples 3-1 to 3-3 except that the fluoroaminosilane synthesized in Synthetic Example 4 was used instead of the inventive aminosilane. The results are also shown in Table 3

Comparative Example 3-2

[0054] A coating solution was prepared and examined as in Examples 3-1 to 3-3 except that $C_8F_{17}CH_2CH_2Si(OCH_3)_3$ was used instead of the inventive aminosilane. The results are also shown in Table 3.

Comparative Example 3-3

[0055] Without applying the coating solution, the glass lens was examined as in Examples 3-1 to 3-3. The results are also shown in Table 3.

Table 3

	Water repellency (deg)	Fingerprint sticking	Fingerprint wiping-off
E 3-1	114	O	O
E 3-2	116	O	O
E 3-3	117	O	O
CE 3-1	97	Δ	Δ
CE 3-2	110	Δ	X
CE 3-3	38	X	X


[0056] It is evident that such coating agent compositions will be applicable to a wide variety of uses as a coating agent having improved water and oil repellency and anti-staining property.

[0057] Japanese Patent Application No. 11-139596 is incorporated herein by reference.

[0058] Although some preferred embodiments have been described, many modifications and variations may be made thereto in the light of the above teachings. It is therefore to be understood that the invention may be practiced otherwise than as described in the specific examples and embodiments.

Claims

1. A perfluoropolyether-modified aminosilane of the following general formula (1):



wherein X^1 and X^2 are hydrolysable groups, R^1 and R^2 are selected from monovalent hydrocarbon groups of 1 to 6 carbon atoms, Q^1 and Q^2 are divalent organic groups, m is an integer from 6 to 50, indices n are (independently) 2 or 3 and x and y are integers from 1 to 3.


2. A perfluoropolyether-modified aminosilane of claim 1 wherein $\text{F}(\text{C}_x\text{F}_{2x}\text{O})_m\text{C}_y\text{F}_{2y}$ is of the following formula (2):




wherein m is as defined above.

3. A perfluoropolyether-modified aminosilane of claim 1 or 2 wherein the hydrolyzable group represented by X is an alkoxy group.
4. A perfluoropolyether-modified aminosilane of claim 1, 2 or 3 wherein Q^1 and Q^2 are selected from $\text{CH}_2\text{CH}_2\text{CH}_2$ or $\text{CH}_2\text{CH}_2\text{NHCH}_2\text{CH}_2\text{CH}_2$.
5. A surface treating agent comprising a perfluoropolyether-modified aminosilane of any one of claims 1 to 4, and/or a partial hydrolytic condensate thereof.
6. An article having on its surface a cured coating primarily comprising cured perfluoropolyether-modified aminosilane of any one of claims 1 to 4 and/or partial hydrolytic condensate thereof.
7. Use of an aminosilane according to any one of claims 1 to 4 and/or a partial hydrolytic condensate thereof, for coating a substrate.
8. Use according to claim 7 in which the substrate is of paper, fabric, metal, glass, plastics or ceramics.

FIG.1





Europäisches Patentamt
Europ an Patent Office
Offic eur p n des brevets



(11) **EP 1 059 320 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
19.12.2001 Bulletin 2001/51

(43) Date of publication A2:
13.12.2000 Bulletin 2000/50

(21) Application number: 00304280.1

(22) Date of filing: 22.05.2000

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 20.05.1999 JP 13959699

(71) Applicant: Shin-Etsu Chemical Co., Ltd.
Chiyoda-ku Tokyo 100 (JP)

(72) Inventors:
• Yamaguchi, Hiromasa,
Shin-Etsu Chemical Co., Ltd.
Usui-gun, Gunma-ken (JP)
• Yamaguchi, Kouichi,
Shin-Etsu Chemical Co., Ltd.
Usui-gun, Gunma-ken (JP)
• Kishita, Hirofumi, Shin-Etsu Chemical Co., Ltd.
Usui-gun, Gunma-ken (JP)

(74) Representative: Stoner, Gerard Patrick et al
MEWBURN ELLIS York House 23 Kingsway
London WC2B 6HP (GB)

(54) **Perfluoropolyether-modified aminosilane, surface treating agent, and aminosilane-coated article**

(57) A novel perfluoropolyether-modified aminosilane cures into a film having improved water and oil re-

pellency, parting and anti-staining properties. A surface treating agent comprising the aminosilane, and an article with a coating of the aminosilane are also provided.

EP 1 059 320 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 30 4280

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	PATENT ABSTRACTS OF JAPAN vol. 007, no. 289 (C-202), 23 December 1983 (1983-12-23) -& JP 58 167597 A (CHISSO KK), 3 October 1983 (1983-10-03) * abstract *	1-8	C08G65/00 C08G65/22 C08G65/32 C09D171/02 C07F7/18
A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 05, 31 May 1999 (1999-05-31) -& JP 11 029585 A (SHIN ETSU CHEM CO LTD), 2 February 1999 (1999-02-02) * abstract *	1-8	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08G C09D C07F
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 24 October 2001	Examiner Marquis, D
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 4280

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-10-2001

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 58167597	A	03-10-1983	NONE	
JP 11029585	A	02-02-1999	NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82